# AT8399

## **High Thermal Conductive Tape**

LiPOLY AT8399 is an unsupported thermally conductive tape with a thermal conductivity of 3.5 W/m\*K. The thickness comes in 0.25~1.0mm, and the AT8399 can withstand 4~13K voltage. Using highly conductive particles makes the tape extremely reliable and easy to use. The stickiness and strength will increase when temperature and pressure rise.

#### **FEATURES**

- / Thermal conductivity:3.5 W/m\*K
- / Excellent adhesive properties
- / Designed for manufacture
- / Excellent long term reliability

#### **TYPICAL APPLICATION**

- / Automotive electronics
- / Telecommunications
- / LED light bar & LED lamp
- / Between any heat-generating
- component and heat sink
- / 5G base station & infrastructure
- / EV electric vehicle

### **TYPICAL PROPERTIES**

PROPERTY	AT8399	TEST METHOD	UNIT
Color	Pink	Visual	-
Reinforced layer	None	-	-
Thickness (Min / Max)	0.25 ~ 1.0	ASTM D374	mm
Density	2.6	ASTM D792	g/cm³
Application temperature	-60~120	-	°C
Short time temp. @30sec	200	-	°C
ROHS	Compliant	_	-
ADHESION			1
Initial tack	12	PSTC-6	cm
Lap shear strength	30	ASTM D1002	N/cm <sup>2</sup>
Die shear strength@25°C	80	-	N/cm <sup>2</sup>
Die shear strength@80°C	40	-	N/cm <sup>2</sup>
Holding power 1kg @25°C	>10000	PSTC-7	min
Holding power 1kg @80°C	>10000	PSTC-7	min
90° Peeling strength @ 25°C, 72 hrs	>7	ASTM D3330	N/inch
90° Peeling strength @ Thermal aging	>12	80°C 1000 hrs	N/inch
90° Peeling strength @ HAST	>20	85°C/85%RH 1000 hrs	N/inch
90° Peeling strength @ Thermal cycling	>11	-40°C~120°C 500 cycles	N/inch
ELECTRICAL			1
Dielectric breakdown (Min / Max)	4 ~ 13	ASTM D149	KV
Surface resistivity	>1010	ASTM D257	Ohm
Volume resistivity	>10°	ASTM D257	Ohm-m
THERMAL		·	
Thermal conductivity	3.5	ASTM D5470	W/m*K
Thermal impedance@5psi (Min / Max)	0.33 ~ 0.98	ASTM D5470	°C-in²/ W
Thermal impedance@10psi (Min / Max)	0.32 ~ 0.97	ASTM D5470	°C-in²/ W
Thermal impedance@15psi (Min / Max)	0.31 ~ 0.93	ASTM D5470	°C-in²/ W

TION SPECIFICATIONS

/ Sheet form / Die-cut parts

Note: All specifications provided by LiPOLY are subject to change without notice. The test methods used by LiPOLY are based on the TIM Tester method and ASTM D5470 test method. These test methods are used as the definition standards for LiPOLY. Property values provided in this document are not for product specifications or guaranteed. This document does not guarantee the performance and quality required for the purchaser's specific purpose. The purchaser needs to evaluate and verify the safety before using the material. We strongly recommend the purchaser pretest the product and verify the performance of the product targets specific conditions. Liability and use of the product are the responsibility of the end user. LiPOLY makes no warranty as to the suitability, mon-infringement of any LiPOLY material or product for any specific or general uses. LiPOLY shall not be liable for incidental orconsequential damages of any kind. All LiPOLY products are sold in accordance with the LiPOLY Terms and Conditions in effect at the time of purchase and a copy of which will be (minished upon request. All ripotts reserved, including LiPOLY trademarks or registered trademarks of LiPOLY or its affiliates. Statements concerning possible or suggested uses made herein shall not be relied upon or be constructed as a guaranty of patent infringement. Copyright 2023 LiPOLY.

