PR28-s



High Insulated Thermal Conductive Film

LiPOLY PR28-s is a very thin, high insulator with a thickness of 0.15mm. It uses Polyimide Film as the reinforcement material, which can increase the tensile strength. It's suitable for high power transistors, electrical equipment, and will be the best choice for auto-distribution systems.

FEATURES


- / Thermal conductivity:2.5 W/m*K / Good insulator
- / Low thermal impedance
- / Reworkable
- / High performance


TYPICAL APPLICATION

- / Power supplies
- / Motor controls
- / Power semiconductors
- / 5G base station & infrastructure
- / EV electric vehicle

SPECIFICATIONS

- / Sheet form
- / Die-cut parts
- / Single-sided adhesive or double-sided adhesive can be used as required





TYPICAL PROPERTIES

PROPERTY	PR28-s	TEST METHOD	UNIT
Color	Gray	Visual	-
Surface tack 2-side/1-side	0	-	-
Reinforced layer	Polyimide	-	-
Thickness	0.10 / 0.125 / 0.15	ASTM D374	mm
Density	1.5	ASTM D792	g/cm³
Hardness	80	ASTM D2240	Shore A
Application temperature	-60~180	-	°C
ROHS & REACH	Compliant	-	-
ELECTRICAL			
Dielectric breakdown	8	ASTM D149	KV
Surface resistivity	>1013	ASTM D257	Ohm
Volume resistivity	>1012	ASTM D257	Ohm-m
THERMAL			
Thermal conductivity	2.5	ASTM D5470	W/m*K
Thermal impedance@20psi	0.342	ASTM D5470	°C-in²/ W
Thermal impedance@60psi	0.269	ASTM D5470	°C-in²/ W
Thermal impedance@100psi	0.235	ASTM D5470	°C-in²/ W

Note: All specifications provided by LiPOLY are subject to change without notice. The test methods used by LiPOLY are based on the TIM Tester method and ASTM D5470 test method. These test methods are used as the definition standards for LiPOLY. Property values provided in this document are not for product specifications or guaranteed. This document does not guarantee the performance and quality required for the purchaser's specific purpose. The purchaser needs to evaluate and verify the performance of the product nave for the product and verify the performance of the product nave for the purchaser pretest the product and verify the performance of the product nave for the purchaser specific conditions. Liability and use of the product are the responsibility of the end user. LiPOLY makes no warranty as to the suitability, merchantability, or non-infringement of any LiPOLY material or product for any specific or general uses. LiPOLY shall not be liable for incidental orconsequential damages of any kind. All LIPOLY products are sold in accordance with the LIPOLY Terms and Conditions in effect at the time of purchase and a copy of which will be (minished upon request. All ripots reserved, including LIPOLY trademarks or registered trademarks of LIPOLY or its affiliates. Statements concerning possible or suggested uses made herein shall not be relied upon or be constructed as a guaranty of patent infringement. Copyright 2023 LIPOLY.